

Textilní zkušební ústav, s.p.

Václavská 237/6, 603 00 Brno, Česká republika  
(Textile Testing Institute)

### TESTING LABORATORY NO. 1001

accredited according to EN ISO/IEC 17025:2005 by Czech institute for accreditation

# TEST REPORT

AZL18/0655-03

**CUSTOMER:** COMPANY "SPLAV" LTD.  
Oktyabrskaya ul.80  
Stroyenie 3, Office 2207  
127521 MOSCOW RUSSIA

**SAMPLE:** Sleeping bag Veil 120  
(according to the customer order) **Filling:** 100% polyester, **Color:** red/yellow,  
**Proportions:** 200x80 cm,  
**Upper material and lining:** 100% Nylon



**SUBJECT OF ASSESSMENT:** Thermal properties of sleeping bags EN ISO 23537-1: 2016

**CONDITIONS OF APPLICATION OF THE TEST REPORT:** Test Report contains results of the tests related to the submitted sample only. Sampling has been done by customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. This Report is a literal translation of the Czech version.

**PREPARED BY:** Švecová  
**CHECKED BY:** Čermáková  
**NUMBER OF PAGES:** 2+1


**DATE OF ACCEPTANCE:**  
20.6. 2018

**DATE OF EXAMINATION:**  
21.6. – 19.7. 2018

**DATE OF ISSUE:**  
20.7. 2018



+420 543 426 722  
+420 543 426 742  
<http://www.tzu.cz>  
[azl@tzu.cz](mailto:azl@tzu.cz)



**PROCEDURE OF ASSESSMENT**

Textilní zkušební ústav, s.p.

***Requirements for sleeping bags – Thermal properties of sleeping bags***

**Test method: EN ISO 23537-1:2016**

**Test conditions:**

- Standard atmosphere for testing: relative humidity 50 -70%, temperature 15 °C
- Thermal manikin: KAREL
- Manikin body surface area: 1,85 m<sup>2</sup>
- Manikin body parameters: body height: 175 cm; body weight: 48 kg
- Manikin body surface temperature: 38 °C
- Position of manikin during testing: in lying position without attached head mask
- Air flow inside the climatic room: 0,1- 0,2 m.s<sup>-1</sup>
- Number of tested specimens: 3x the same sample
- Artificial ground: manikin laying on rigid mattress (R<sub>ct</sub> = 0,85 m<sup>2</sup>. K.W<sup>-1</sup>)
- Manikin garment: two-piece suit (R<sub>ct</sub> = 0,051 m<sup>2</sup>.K.W<sup>-1</sup>); knee-length socks (R<sub>ct</sub> = 0,058 m<sup>2</sup>.K.W<sup>-1</sup>)

**TEST RESULTS**


<b>Sleeping bag Veil 120</b> <b>Filling: 100% polyester, Color: red/yellow, Proportions: 200x80 cm,</b> <b>Upper material and lining: 100% Nylon</b>			
Characteristics	Test method	Measuring Unit	Values identified
<b>Standard thermal insulation R<sub>c</sub> (1)</b> - average value - coefficient of variation	<b>EN ISO 23537-1:2016</b>	m <sup>2</sup> . K.W <sup>-1</sup> %	0,612 0,34

**Lower temperature limits of the range of utility:**

Comfort temperature T <sub>comf</sub> <sup>(3)</sup>	Limit temperature T <sub>lim</sub> <sup>(2)</sup>	Extreme temperature T <sub>ext</sub> <sup>(1)</sup>
13,5°C	10,0 °C	-1,1 °C

- (1) extreme temperature - lower extreme temperature where the risk of health damage by hypothermia occurs  
 (2) limit temperature - lower limit at which a sleeping bag user with a curled up body posture is globally in thermal equilibrium and just not feeling cold  
 (3) comfort temperature - lower limit of the comfort range, down to which a sleeping bag user with a relaxed posture, such as lying on their back, is globally in thermal equilibrium and just not feeling cold


**Graph for the range of utility**



**WARNING: In the risk range a strong sensation of cold has to be expected. There is a risk of health damage by hypothermia.**

All values of uncertainty of measurement were calculated with assumption of normal distribution. For purposes of calculation of expanded uncertainty values will be multiplied by coverage factor k=2 for statistical level 95%. Sampling was not taken into consideration





Annex:

**Warning of misuse of temperature rating**

The insulation of a sleeping bag varies widely with the conditions of use (wind, radiating ambience, posture and clothing of the sleeping bag user, ground insulation, eventual humidity in the sleeping bag etc.), and perception of cold is also individually different (influence of acclimatisation, physical and psychological state, food etc.).

The limiting temperatures of the range of utility as determined in the EN ISO 23537-1: 2016 only compare performance of sleeping bags with regard to standardised test conditions. They do not take into account all possible variations in conditions of use and in individual reactions, and therefore should be considered only as a guideline, that needs personal adaptation for practical use.

In particular, it shall be noted that the extreme temperature is a very theoretical limit. It shall therefore only be considered as a point of danger that should not be approached - unless the sleeping bag user has a wide personal experience.

The determination of the comfort temperature uses the available knowledge of published data, based on the thermal balance of the whole body. The human body is very sensitive to local discomfort: a local thermal bridge may not influence the global insulation of the sleeping bag, but might greatly affect the sensation of cold of the sleeping bag user. It shall be emphasised that the test method in the EN ISO 23537-1: 2016 does not provide any guarantee against local cooling.

The temperatures of the range of utility relate to indoor conditions. For outdoor use, wind may affect insulation of the bag to a large extent, especially if the shell fabric of the sleeping bag is air permeable.

In the EN ISO 23537-1: 2016, sleeping bags are considered as dry. High moisture content might lower thermal performance.

Petr Nasadil  
Head of Testing Laboratory

